

Docket No. 20661-801D1

IN THE CLAIMS

Please amend the claims as follows:

1. (Twice Amended) A resistor having a resistance that can be adjusted by current being passed there through and which is formed as part of a semiconductor device comprising:

C1
a polycrystalline silicon resistor formed of and on a layer, wherein said polysilicon resistor is formed using a doping wherein said doping has a concentration of from $\sim 6 \times 10^{19} \text{ cm}^{-3}$ to $\sim [3.75] 1 \times 10^{20} \text{ cm}^{-3}$ and wherein said polycrystalline silicon resistor has at least a first and second order temperature coefficient wherein the sign of said first and second order temperature coefficients are opposite each other; and

Sub D'
wherein said resistor resistance is electronically trimmed.

2. (Twice Amended) A resistor having a resistance that can be adjusted by current being passed there through and which is formed as part of a semiconductor device comprising:

a polycrystalline silicon resistor formed of on a layer, wherein said polysilicon resistor is formed using a doping wherein said doping has a concentration of less than $\sim 3.75 \times 10^{20} \text{ cm}^{-3}$ and wherein said polycrystalline silicon resistor has at least a first and second order temperature coefficient, wherein the sign of said first and second order temperature coefficients are opposite each other; and

wherein said resistor resistance is electronically trimmed.

Docket No. 20661-801D1

01 amended
11. (Twice amended) A resistor having a resistance that can be adjusted by current being passed there through and which is formed as part of a semiconductor device comprising:

a polycrystalline silicon resistor formed of on a layer, wherein said polysilicon resistor is formed using a doping wherein said doping has a concentration of greater than $\sim 6 \times 10^{19} \text{ cm}^{-3}$ and wherein said polycrystalline silicon resistor has at least a first and second order temperature coefficient, wherein the sign of said first and second order temperature coefficients are opposite each other; and

wherein said resistor resistance is electronically trimmed.

12. (Twice amended) A resistor having a resistance that can be adjusted by current being passed there through and which is formed as part of a semiconductor device comprising:

a polycrystalline silicon resistor formed of on a layer, wherein said polysilicon resistor is formed using a late implant doping technique and wherein said polycrystalline silicon resistor has at least a first and second order temperature coefficient, wherein the sign of said first and second order temperature coefficients are opposite each other; and

wherein said resistor resistance is electronically trimmed.